

## PREPARATION AND CHARACTERIZATION OF Eu-MAGADIITE INTERCALATION COMPOUNDS

NAOKO MIZUKAMI<sup>1</sup>, MASASHI TSUJIMURA<sup>1</sup>, KAZUYUKI KURODA<sup>1,2</sup> AND MAKOTO OGAWA<sup>3,4,\*</sup>

<sup>1</sup> Department of Applied Chemistry, Waseda University, Ohkubo 3-4-1, Shinjuku-ku, Tokyo 169-8555, Japan

<sup>2</sup> Kagami Memorial Laboratory for Materials Science and Technology, Waseda University, Nishiwaseda 2-8-26, Shinjuku-ku, Tokyo 169-0051, Japan

<sup>3</sup> PRESTO, Japan Science and Technology Corporation (JST)

<sup>4</sup> Department of Earth Sciences, Waseda University, Nishiwaseda 1-6-1, Shinjuku-ku, Tokyo 169-8050, Japan

**Abstract**—The intercalation of europium ions (Eu<sup>3+</sup>) into the interlayer space of a layered silicate, magadiite, was conducted by ion-exchange reactions between magadiite and europium(III) chloride. X-ray diffraction and elemental analysis indicated that Eu<sup>3+</sup> cations were intercalated into the interlayer space of magadiite. The ion exchange between Eu<sup>3+</sup> and Na<sup>+</sup> occurred preferentially so that the adsorbed Eu<sup>3+</sup> amounts were controlled quantitatively. Thermal transformation of the original layered structure was suppressed by the intercalation of Eu<sup>3+</sup>. The resulting intercalation compounds exhibited photoluminescence arising from the intercalated Eu<sup>3+</sup>. The luminescence intensity varied in accordance with the amount of Eu<sup>3+</sup> adsorbed, suggesting that the self-quenching occurred at higher loading levels. The luminescence intensity was also changed by the heat treatment, corresponding to the change in the surroundings of the Eu<sup>3+</sup> adsorbed, induced by the removal of the adsorbed water molecules and the hydroxyl groups of the silicate.

**Key Words**—Europium, Intercalation, Luminescence, Magadiite, Nanocomposite.

### INTRODUCTION

Intercalation is a method by which to synthesize hybrid materials with a wide range of chemical compositions and low dimensional nanostructures. The reaction can also be applied to the sequestration of toxic and/or noble materials from different environments. Magadiite (ideal formula Na<sub>2</sub>Si<sub>14</sub>O<sub>29</sub>·nH<sub>2</sub>O) is a layered silicate capable of incorporating guest species in the interlayer space to form intercalation compounds (Eugster, 1967; Lagaly, 1979). The cation-exchange properties of magadiite have been investigated and the nature of the cation exchange sites have been documented, though the quantitative evaluation is still controversial.

Magadiite possesses some unique properties for organizing guest species. (1) The surface silanol groups bear the cation exchange sites and the layer charge density is relatively high (~220 meq/100 g magadiite). (2) Magadiite can be conveniently prepared in a laboratory by hydrothermal synthesis as purely siliceous materials. Taking advantage of these characteristic features of magadiite, the introduction of functional species into magadiite has been reported together with fundamental studies on the intercalation reaction and the structures of intercalation compounds (Lagaly *et al.*, 1975a,b; Ruiz-Hitzky and Rojo, 1980; Ogawa *et al.*, 1998a,b; Isoda *et al.*, 2000; Kim *et al.*, 1997; Landis *et al.*, 1991; Dailey and Pinnavaia, 1992; Wang *et al.*, 1998). The organization of photoactive species on the surface of layered materials has been investigated to

construct photofunctional supramolecular systems (Ogawa and Kuroda, 1995). Along this line, the luminescence of the ruthenium tris(bipyridine) complex and the photochromism of cationic azobenzene derivatives have been reported previously (Ogawa and Maeda, 1998; Ogawa and Takizawa, 1999; Ogawa *et al.*, 2001a,b).

In this paper, we report the intercalation of Eu<sup>3+</sup> ions into magadiite by ion-exchange reactions. Rare earth element-doped solids have been investigated extensively as possible advanced materials in applications such as luminescent, catalytic, sensing and possible optical recording materials (Bredol *et al.*, 1991). The immobilization of rare earth elements (*REE*) in various solid matrices including silica glasses (Zaitoun *et al.*, 2000), organosilicate gels (Nogami and Abe, 1997), zeolites (Arakawa *et al.*, 1979; Suib and Carrado, 1985; Bartlett *et al.*, 1988; Suib *et al.*, 1984), and organic polymers (Smirnov *et al.*, 1999) has been reported so far. Among possible solid matrices, crystalline inorganic solids are attractive due to the stability and well-defined microstructures. Accordingly, the introduction of *REE* into low-dimensional inorganic solids have been investigated in order to control the electronic properties of conducting oxides as well as to optimize optical properties of the doped solids (Kudo and Sakata, 1995; Honma *et al.*, 1998; Kudo, 1997).

The luminescence of rare earth ions doped in crystalline inorganic solids has been reported (Bredol *et al.*, 1991). The concentration quenching of the luminescence caused by the excitation energy migration has already been observed in the systems of rare earth

\* E-mail address of corresponding author: makato@waseda.ac.jp

Table 1. Chemical composition of Eu<sup>3+</sup>-magadiites.

Concentration of EuCl <sub>3</sub> solution mmol/L	Adsorbed Eu <sup>3+</sup> / Added Eu <sup>3+</sup> (%)	Eu <sup>3+</sup> /14Si	Adsorbed Eu <sup>3+</sup> /CEC (%)
0.77	83	0.14	21
1.2	90	0.24	36
1.5	98	0.33	49
2.3	97	0.48	73
30		0.65	98
30 × 3*		0.68	100

\* Ion exchange was repeated three times

ions-doped solids (Honma, *et al.*, 1998). It is vital for optimum performance to control the separation of adjacent rare earth ions. Although one can expect a wide range of chemical compositions and microstructures, studies on the introduction of *REE* into inorganic solids via soft chemical approach are limited (Bergaya and Van Damme, 1983; Constantino *et al.*, 1998). The ion exchange of rare earth ions into ion exchangeable crystalline inorganic solids is worth investigating from the viewpoints of spatial control of the rare earth ions as well as the recovery of rare elements from different environments (Miller *et al.*, 1982).

## EXPERIMENTAL SECTION

### Materials

Na-magadiite was synthesized hydrothermally from colloidal silica and NaOH, as described previously

(Okutomo *et al.*, 1999). Europium(III) chloride was purchased from Tokyo Kasei Industries Co. and used without further purification.

### Sample preparation

Intercalation of Eu<sup>3+</sup> into magadiite was carried out by conventional ion-exchange reactions in which an




Figure 2. Luminescence spectra of Eu<sup>3+</sup>-magadiites. Eu/Si = 0.48 (a), 0.33 (b), 0.68 (c), 0.65 (d), 0.24 (e) and 0.14 (f).




Figure 3. The relationship between the intensity of <sup>5</sup>D<sub>0</sub>-<sup>7</sup>F<sub>2</sub> luminescence band (at 614 nm) and the amount of Eu<sup>3+</sup> adsorbed.




Figure 4. TG curves of  $\text{Eu}^{3+}$ -magadiites.  $\text{Eu}/\text{Si} = 0.14$  (a), 0.24 (b), 0.33 (c), 0.48 (d) and 0.68 (e).

aqueous suspension of magadiite was mixed with an aqueous solution of europium(III) chloride ( $\text{pH} \approx 5$ ) and the mixture was allowed to react for 1 day at room temperature. After centrifugation, the resulting solid was washed with ethanol and dried at  $40^\circ\text{C}$  for 2 days. The products were heat treated in air at  $400\text{--}1500^\circ\text{C}$ .

#### Characterization

Powder X-ray diffraction (XRD) patterns were obtained on a Mac Science,  $\text{MXP}^3$  diffractometer using




Figure 6. Powder XRD patterns of Na-magadiite before (a) and after the heat treatment at 600 (b), 800 (c), 900 (d), 1000 (e), 1300 (f) and  $1500^\circ\text{C}$  (g).




Figure 5. DTA curves of  $\text{Eu}^{3+}$ -magadiites.  $\text{Eu}/\text{Si} = 0.14$  (a), 0.24 (b), 0.33 (c), 0.48 (d) and 0.68 (e).

monochromatic  $\text{CuK}\alpha$  radiation. Steady-state luminescence spectra were recorded on a Hitachi F-4500 fluorospectrophotometer with the excitation wavelength of 394 nm. The chemical composition was determined by inductively coupled plasma (ICP) analysis (Seiko SPS7000A) after the samples were dissolved with  $\text{HF}$ ,  $\text{HNO}_3$  and  $\text{H}_2\text{SO}_4$ . Scanning electron micrographs (SEM) were obtained using an HITACHI S-2500CX scanning electron microscope. Thermogravimetry-differential thermal analysis (TG-DTA) curves were recorded




Figure 7. Powder XRD patterns of  $\text{Eu}^{3+}$ -magadiite ( $\text{Eu}/\text{Si} = 0.33$ ) before (a) and after the heat treatment at 600 (b), 800 (c), 900 (d), 1000 (e), 1300 (f) and  $1500^\circ\text{C}$  (g).




Figure 8. Powder XRD patterns of  $\text{Eu}^{3+}$ -magadiite ( $\text{Eu/Si} = 0.48$ ) before (a) and after the heat treatment at 600 (b), 800 (c), 900 (d), 1000 (e), 1300 (f) and 1500°C (g).

on a Mac Science TG-DTA 2000S instrument at a heating rate of  $10^\circ\text{C min}^{-1}$  under a dry air atmosphere using  $\alpha$ -alumina ( $\alpha\text{-Al}_2\text{O}_3$ ) as the standard material. Transmission electron micrographs (TEM) were obtained on an HITACHI H8100 transmission electron microscope with accelerating voltage 200 kV.

## RESULTS AND DISCUSSION

The chemical compositions of the products are summarized in Table 1. The loaded  $\text{Eu}^{3+}$  cations were almost quantitatively adsorbed on magadiite. Hereafter, the products were denoted as  $\text{Eu}^{3+}$ -magadiite ( $n$ ), where  $n$  indicates the molar ratio of  $\text{Eu}^{3+}$  to the  $\text{Si}_{14}\text{O}_{29}$  unit of magadiite. The XRD patterns of the products are shown in Figure 1, together with that of original Na-magadiite. The basal spacing decreased from 1.56 nm to 1.42 nm after reaction with europium(III) chloride, suggesting the change in the hydration of the interlayer space from the highly hydrophilic Na-form to Eu-form. When the amount of  $\text{Eu}^{3+}$  loaded was small, two diffraction peaks were observed; one corresponds to the hydrated Na-magadiite (1.56 nm) and the other is ascribable to the  $\text{Eu}^{3+}$ -exchanged phase ( $\sim 1.4$  nm). Since the thickness of the silicate layer is 1.12 nm, as estimated from the basal spacing of the dehydrated H-magadiite (Rojo *et al.*, 1988), the gallery height of the  $\text{Eu}^{3+}$ -magadiites was estimated, from the observed basal spacing, to be 0.3 nm. The value is large enough to accommodate hydrated  $\text{Eu}^{3+}$  ions.

The luminescence spectra of the  $\text{Eu}^{3+}$ -magadiites (0.65) are shown in Figure 2. In the spectra, the




Figure 9. Powder XRD patterns of  $\text{Eu}^{3+}$ -magadiite ( $\text{Eu/Si} = 0.68$ ) before (a) and after the heat treatment at 600 (b), 800 (c), 900 (d), 1000 (e), 1300 (f) and 1500°C (g).

luminescence bands ascribable to the  $^5\text{D}_0\text{-}^7\text{F}_1$ ,  $^5\text{D}_0\text{-}^7\text{F}_2$ ,  $^5\text{D}_0\text{-}^7\text{F}_3$  and  $^5\text{D}_0\text{-}^7\text{F}_4$  transitions of  $\text{Eu}^{3+}$  were observed at 592, 614, 655 and 702 nm, respectively. The relative luminescence intensity depends on the strength and symmetry of the electric field around the  $\text{Eu}^{3+}$  ions. The relative intensity ratio of each transition changed only slightly depending on the amounts  $\text{Eu}^{3+}$  adsorbed in the present system, showing that the  $\text{Eu}^{3+}$  ions adsorbed in a similar manner. The small difference in the relative luminescence intensity was thought to be caused by such parameters as water content and  $\text{Eu}^{3+}$ - $\text{Eu}^{3+}$  interactions.

Figure 3 shows the relationship between the intensity of the  $^5\text{D}_0\text{-}^7\text{F}_2$  luminescence band (at 614 nm) and the amount of  $\text{Eu}^{3+}$  adsorbed. The intensity was normalized by the amount of  $\text{Eu}^{3+}$ , as in the equation  $I_n = I_m/m$ ; where  $I_n$ ,  $I_m$  and  $m$  denote normalized luminescence intensity, observed luminescence intensity, and the amount of  $\text{Eu}^{3+}$  adsorbed, respectively. With the increase in the amount of  $\text{Eu}^{3+}$ , the luminescence was intensified and the maximum intensity was recorded for the  $\text{Eu}^{3+}$ -magadiite (0.33). Further increase in the amount of  $\text{Eu}^{3+}$  resulted in a weakening of the luminescence. This observation is explained by the concentration quenching at the higher  $\text{Eu}^{3+}$  loadings. Similar phenomena have been observed for the other  $\text{Eu}^{3+}$ -doped low dimensional oxide systems (Kudo and Sakata, 1995; Honma *et al.*, 1998; Kudo, 1997).

Water molecules and hydroxyl groups deactivate the excited states of  $\text{Eu}^{3+}$  to cause quenching of the luminescence. In the present system,  $\text{Eu}^{3+}$  cations are located in the interlayer space where adsorbed water molecules and hydroxyl groups (silanol groups) are present. In order to observe the effect of the interlayer




Figure 10. SEM images of Na-magadiite before (a) and after the heat treatment at 900 (b), 1200 (c) and 1500°C (d). Scale bars in a, b and c = 5  $\mu\text{m}$ ; in d, scale bar = 25  $\mu\text{m}$ .

microenvironments on the luminescence characteristics, the products were heated in air. The TG and DTA curves of the products are shown in Figures 4 and 5, respectively. The desorption of adsorbed water occurred below 200°C and the dehydroxylation of silanol groups occurred at higher temperatures (250–800°C) as shown in the TG curves. As reported previously by Muraishi (1999), the phase transformation of Na-magadiite into quartz, cristobalite and tridymite occurred above 700°C. The thermal behavior of the products changed after the introduction of  $\text{Eu}^{3+}$ . With the increase in the  $\text{Eu}^{3+}$  content, the exothermic peaks ascribable to the phase transition (in the temperature range 750–950°C) appeared at higher temperatures (Figure 5).

The variation in the XRD patterns, after heat treatment, is shown in Figures 6–9 for Na-magadiite and  $\text{Eu}^{3+}$ -magadiites. The phase transition temperature increased with the increase in the  $\text{Eu}^{3+}$  content as shown in Figure 6. For the  $\text{Eu}^{3+}$ -magadiite (0.68), the diffraction peaks ascribable to the layered structure remained at

900°C, while Na-magadiite and  $\text{Eu}^{3+}$ -magadiites with lower  $\text{Eu}^{3+}$  contents transformed into cristobalite and tridymite at lower temperatures.

Scanning electron micrographs of magadiite and  $\text{Eu}^{3+}$ -magadiite (0.68) are shown in Figures 10a and 11a, respectively. The rosette morphology composed of platelet particles of original magadiite was retained during the ion exchange with  $\text{Eu}^{3+}$ . After the heat treatments, the morphology changed, as shown in Figures 11b–d and 12b–d. The original morphology of magadiite was lost below 900°C for magadiite while the morphology of  $\text{Eu}^{3+}$ -magadiite (0.68) remained up to 1200°C. These observations were consistent with the XRD results, confirming that the transformation of the silicate layers was suppressed by the presence of  $\text{Eu}^{3+}$  ions in the interlayer space.

When  $\text{Eu}^{3+}$ -magadiite (0.68) was heated above 900°C, new diffraction peaks appeared in addition to those ascribable to cristobalite. These diffraction peaks appeared at positions close to those of  $\text{NaSm}_9(\text{SiO}_4)_6\text{O}_2$




Figure 11. SEM images of  $\text{Eu}^{3+}$ -magadiite (0.65) before (a) and after the heat treatment at 900 (b), 1200 (c) and 1500°C (d). All scale bars = 5  $\mu\text{m}$ .

(JCPDS 32-1147). Similar diffraction peaks appeared after the heat treatment above 1200°C for the  $\text{Eu}^{3+}$ -magadiites with lower  $\text{Eu}^{3+}$  content, and the diffraction intensity was in accordance with the  $\text{Eu}^{3+}$  content. Consequently, the diffraction peaks were thought to be due to a crystalline phase ( $\text{NaEu}_9(\text{SiO}_4)_6\text{O}_2$ ) of the structure similar to  $\text{NaSm}_9(\text{SiO}_4)_6\text{O}_2$ .

The luminescence intensity of the heated products is summarized in Figure 12. The luminescence was intensified up to 500°C irrespective of the  $\text{Eu}^{3+}$  contents, showing that the removal of the adsorbed water and hydroxyl groups located close to the interlayer  $\text{Eu}^{3+}$  ions. Heat treatment at higher temperatures (>700°C) results in weakened luminescence. This observation might account for the aggregation of  $\text{Eu}^{3+}$ . During the transformation of the silicate layers,  $\text{Eu}^{3+}$  ions are separated to form a  $\text{Eu}^{3+}$ -rich phase while the silica layers form a purely siliceous crystalline phase such as quartz and cristobalite as shown in Figures 6–9. As a

result of the phase separation, concentration quenching occurred leading to a weakening of the luminescence intensity.

## CONCLUSIONS

The intercalation of  $\text{Eu}^{3+}$  ions into the interlayer space of magadiite has been conducted by ion-exchange reactions in aqueous media. The luminescence of the adsorbed  $\text{Eu}^{3+}$  ions was observed for the intercalation compounds. The luminescence intensity varied depending on the loaded Eu amounts as well as the heat treatment, indicating the concentration quenching and the quenching by the adsorbed water and hydroxyl groups in the system. Thus, the present Eu-magadiite intercalation compounds can be regarded as novel types of Eu-doped silicas. The layered structure of magadiite was stabilized by the introduction of Eu ions in the interlayer space.




Figure 12. Variation of normalized luminescence intensity of  $\text{Eu}^{3+}$ -magadiites as a function of the heat treatment temperature.

#### ACKNOWLEDGMENTS

The present work was partially supported by Waseda University as a Special Project Research and Grant-in-Aid for COE Research, Ministry of Education, Culture, Sports, Science and Technology (MEXT). The authors are grateful to Dr R. Miyawaki (National Museum of Japan) for the discussion about the crystalline structures of Eu-silicates.

#### REFERENCES

- Arakawa, T., Tagata, T., Adachi, G. and Shiohara, J. (1979) Photoluminescence during the catalysis of water decomposition on an activated europium(III)-Y zeolite. *Journal of the Chemical Society, Chemical Communications*, 453–454.
- Bartlett, J.R., Cooney, R.P. and Kydo, R.A. (1988) Europium-exchanged synthetic faujasite zeolites: A luminescence spectroscopic study. *Journal of Catalysis*, **114**, 58–70.
- Bergaya, F. and Van Damme, H. (1983) Luminescence of  $\text{Eu}^{3+}$  and  $\text{Tb}^{3+}$  ions adsorbed on hydrated layer-lattice silicate surfaces. *Journal of the Chemical Society, Faraday Transactions 2*, **79**, 505–518.
- Bredol, M., Kynast, U. and Ronda, C. (1991) Designing luminescent materials. *Advanced Materials*, **3**, 361–367.
- Constantino, V.R.L., Bizeto, M.A. and Brito, H.F. (1998) Photoluminescence study of layered niobates intercalated with  $\text{Eu}^{3+}$  ions. *Journal of Alloys and Compounds*, **278**, 142–148.
- Dailey, J.S. and Pinnavaia, T.J. (1992) Silica pillared derivatives of  $\text{H}^{+}$ -magadiite, a crystalline hydrated silica. *Chemistry of Materials*, **4**, 855–863.
- Eugster, H.P. (1967) Hydrous sodium silicates from Lake Magadii, Kenya: Precursors of bedded chert. *Science*, **157**, 1177–1180.
- Honma, T., Toda, K., Ye, Z-G. and Sato, M. (1998) Concentration quenching of the  $\text{Eu}^{3+}$ -activated luminescence in some layered perovskites with two-dimensional arrangement. *Journal of Physics and Chemistry of Solids*, **59**, 1187–1193.
- Isoda, K., Kuroda, K. and Ogawa, M. (2000) Grafting of  $\gamma$ -methacryloxypropylsilyl groups in the interlayer space of layered polysilicate magadiite and the copolymerized products with methylmethacrylate. *Chemistry of Materials*, **12**, 1702–1707.
- Kim, C.S., Yates, D.M. and Heaney, P.J. (1997) The layered sodium silicate magadiite: An analog to smectite for benzene sorption from water. *Clays and Clay Minerals*, **45**, 881–885.
- Kudo, A. and Sakata, T. (1995) Luminescent properties of nondoped and rare earth metal ions-doped  $\text{K}_2\text{La}_2\text{Ti}_3\text{O}_{10}$  with layered perovskite structures: importance of the hole trap process. *Journal of Physical Chemistry*, **99**, 15963–15967.
- Kudo, A. (1997) Luminescent properties of nondoped and rare earth metal ions-doped  $\text{KLaNb}_2\text{O}_7$  with layered perovskite structures. *Chemistry of Materials*, **9**, 664–669.
- Lagaly, G. (1979) Crystalline silicic acids and their interface reactions. *Advances in Colloid and Interface Science*, **11**, 105–148.
- Lagaly, G., Beneke, K. and Weiss, A. (1975a) Magadiite and H-magadiite: i. Sodium magadiite and some of its derivatives. *American Mineralogist*, **60**, 642–649.
- Lagaly, G., Beneke, K. and Weiss, A. (1975b) Magadiite and H-magadiite: ii. H magadiite and its intercalation compounds. *American Mineralogist*, **60**, 650–658.
- Landis, M.E., Aufdembrink, B.A., Chu, P., Johnson, I.D., Kirker, G.W. and Rubin, M.K. (1991) Preparation of molecular sieves from dense, layered metal oxides. *Journal of the American Chemical Society*, **113**, 3189–3190.
- Miller, S.E., Heath, G.R. and Gonzalez, R.D. (1982) Effects of temperature on the sorption of lanthanides by montmorillonite. *Clays and Clay Minerals*, **30**, 111.
- Muraishi, H. (1999) Effects of the exchangeable alkali metal ions on the thermal behavior of magadiite and kenyaite. *Nendo Kagaku*, **38**, 188–196.
- Nogami, M. and Abe, Y. (1997) High temperature persistent spectral hole burning of  $\text{Eu}^{3+}$ -doped  $\text{SiO}_2$  glass prepared by the sol-gel process. *Applied Physics Letters*, **71**, 3465–3467.
- Ogawa, M. and Kuroda, K. (1995) Photofunctions of intercalation compounds. *Chemical Reviews*, **95**, 399–438.
- Ogawa, M. and Maeda, N. (1998) Intercalation of tris(bipyridine)ruthenium(II) into magadiite. *Clay Minerals*, **33**, 643–650.
- Ogawa, M. and Takizawa, Y. (1999) Intercalation of tris(2,2'-bipyridine)ruthenium(II) into a layered silicate, magadiite, with the aid of a crown ether. *Journal of Physical Chemistry, B*, **103**, 5005–5009.
- Ogawa, M., Okutomo, S. and Kuroda, K. (1998a) Control of interlayer microstructures of a layered silicate by surface modification with organochlorosilanes. *Journal of the American Chemical Society*, **120**, 7361–7362.
- Ogawa, M., Miyoshi, M. and Kuroda, K. (1998b) Perfluoroalkylsilylation of a layered silicate, magadiite. *Chemistry of Materials*, **10**, 3787–3791.
- Ogawa, M., Ishii, T., Miyamoto, N. and Kuroda, K. (2001a) Photocontrol of the basal spacing of azobenzene-magadiite intercalation compound. *Advanced Materials*, **13**, 1107–1109.
- Ogawa, M., Yamamoto, M. and Kuroda, K. (2001b) Intercalation of an amphiphilic azobenzene derivative into the interlayer space of a layered silicate, magadiite. *Clay Minerals*, **36**, 263–267.
- Okutomo, S., Kuroda, K. and Ogawa, M. (1999) Preparation of dimethylalkylsilylated-magadiites. *Applied Clay Science*, **15**, 253–264.
- Rojo, J.M., Ruiz-Hitzky, E. and Sanz, J. (1988) Proton-sodium exchange in magadiite. Spectroscopic study (NMR, IR) of the evolution of interlayer OH groups. *Inorganic Chemistry*, **27**, 2785–2790.
- Ruiz-Hitzky, E. and Rojo, M. (1980) Intracrystalline grafting on layer silicic acid. *Nature*, **287**, 28–30.

- Ruiz-Hitzky, E., Rojo, M. and Lagaly, G. (1985) Mechanism of the grafting of organosilanes on mineral surfaces. *Colloid Polymer Science*, **263**, 1025–1030.
- Smirnov, V.A., Sukhadolski, G.A., Philippova, O.E. and Khokhlov, A.R. (1999) Use of luminescence of europium ions for the study of the interactions of polyelectrolyte hydrogels with multivalent cations. *Journal of Physical Chemistry, B*, **103**, 7621–7626.
- Suib, S.L. and Carrado, K.A. (1985) Zeolite photochemistry: Energy transfer between rare-earth and actinide ions in zeolites. *Inorganic Chemistry*, **24**, 200–202.
- Suib, S.L., Zerger, R.P., Morrison, T.I. and Shenoy, G.K. (1984) *Journal of Chemical Physics*, **80**, 2203–2207.
- Wang, Z., Lan, T. and Pinnavaia, T.J. (1998) Hybrid organic-inorganic nanocomposites: exfoliation of magadiite nanolayers in an elastomeric epoxy polymer. *Chemistry of Materials*, **10**, 1820–1826.
- Zaitoun, M.A., Goken, D.M., Bailey, L.S., Kim, T. and Lin, C.T. (2000) Thermoanalysis and emission properties of  $\text{Eu}^{3+}/\text{Eu}^{2+}$  in  $\text{Eu}^{3+}$ -doped xerogels. *Journal of Physical Chemistry, B*, **104**, 189–196.

(Received 5 October 2001; revised 5 June 2002; Ms. 591; A.E. James E. Amonette)